

陶瓷纤维 喷吹式 棉毯

陶瓷纤维 离心式 棉毯



产品名称		1260°C-S 棉毯	1400°C-S 棉毯	1600°C 棉毯
最高使用温度		1260°C 2300°F	1425° C 2600°F	1593° C 2900°F
密度 (Kg/M3)		6P, 8P 96, 128	6P, 8P 96, 128	6P, 8P 96, 128
尺寸 (mm)		6x600x7200, 13x600x7200 25x600x7200 50x600x3600	25x600x7200 50x600x3600	12.5x600x3600 25x600x3600
Kg/cm ² 伸张强度	4P 64KG/M ³	0.4	0.4	-----
	6P 96KG/M ³	0.8	0.8	0.95
	8P 128KG/M ³	1.05	1.05	1.05
Kcal/mh. 热传导率 °C	密度	6P 8P	6P 8P	6P 8P
	400° C	0.0946 0.086	0.0945 0.086	0.0688 0.0688
	600° C	0.1376 0.129	0.1376 0.129	0.1118 0.1032
	800° C	0.1978 0.172	0.1978 0.172	0.1634 0.1462
	1000° C	0.2752 0.2322	0.2752 0.2322	0.2322 0.2064
	1200° C 1400° C	----- -----	----- -----	0.387 0.3268 0.5762 0.4816
化学成份%	Al ₂ O ₃	46	43	96
	SiO ₂	54	54	4
	ZrO ₂	-----	-----	-----
	CaO	-----	-----	-----
	MgO	-----	-----	-----
	Cr ₂ O ₃	-----	3	-----

6mmt 密度 8P 棉毯

Your Solution for Insulation Since 1989 !