

Ceramic Fiber Blanket

Thermotech 工德

+886-3-4644666 Fax: +886-3-4644578 E-mail: kumtek@ms13.hinet.net www.kumtek.com.tw

CERAMIC FIBER B BLANKET

陶瓷纤维 喷吹式 棉毯

CERAMIC FIBER S BLANKET

陶瓷纤维 离心式 棉毯



产品名称 PRODUCTS		1260°C-S BLANKET	1400 -S BLANKET	1600 BLANKET
最高工作温度 MAX. TEMP.		1260 2300	1425 2600	1593 2900
密度 DENSITY(Kg/M3)		6p 8P 同 右	6P 8P 同 右	6P, 8P 96, 128
尺寸 SIZE(mm)		6x600x7200, 13x600x7200 25x600x7200 50x600x3600	25x600x7200 50x600x3600	12.5x600x3600 25x600x3600
H TENSILE STRENGTH KG/cm ² 伸张强度	4P 64KG/M ³	0.4	0.4	-----
	6P 96KG/M ³	0.8	0.8	0.95
	8P128/KG/M ³	1.05	1.05	1.05
THERMAL CONDUCTIVITY 热传导率 Kcal/mh	DENSITY	6P 8P	6P 8P	6P 8P
	400	0.0946 0.086	0.0945 0.086	0.0688 0.0688
	600	0.1376 0.129	0.1376 0.129	0.1118 0.1032
	800	0.1978 0.172	0.1978 0.172	0.1634 0.1462
	1000	0.2752 0.2322	0.2752 0.2322	0.2322 0.2064
	1200	-----		0.387 0.3268
CHEMICAL ANALYSIS % 化学成份	1400	-----	-----	0.5762 0.4816
	AL ₂ O ₃	46	43	96
	SiO ₂	54	54	4
	ZrO ₂	-----	-----	-----
	CaO	-----	-----	-----
	MgO	-----	-----	-----
	Cr ₂ O ₃	-----	3	-----
其它 Others	微量 TRACE	微量 TRACE	-----	

6mmt Blanket available in 8P density only.